Application No.: 10/593,624
Art Unit: 1794
Amendment under 37 CFR §1.116
Attorney Docket No.: 062926

## **AMENDMENTS TO THE CLAIMS**

The listing of claims below replaces all prior versions of claims in the application.

1. (Currently Amended): An R-Fe-B alloy based thin film magnet comprising an R-Fe-B based alloy which contains 28 to 45 percent by mass of R element (where R represents at least one type of rare-earth lanthanide elements) and which is physically formed into an alloy film,

wherein the alloy film has a thickness is 0.2 to 400 µm, and

wherein the R-Fe-B based alloy has a composite texture comprising  $R_2Fe_{14}B$  crystals grown by heat treatment of said alloy film and having a crystal grain diameter of [[0.5]]  $\underline{3}$  to 30  $\mu$ m and R-element-rich grain boundary phases formed by the heat treatment present at boundaries between the crystals, and having a nucleation type coercive force.

- 2. (Previously Presented): The R-Fe-B alloy based thin film magnet according to Claim 1, wherein c axes, which are easy-to-magnetize axes, of R<sub>2</sub>Fe<sub>14</sub>B crystals are oriented randomly or oriented nearly perpendicularly to a film surface.
  - 3. (Cancelled):
- 4. (Withdrawn-Currently Amended): A method for preparation of the R-Fe-B alloy based thin film magnet according to any one of Claims 1 to 3 one of Claim 1 or 2, the method comprising the step of heating the R-Fe-B based alloy in a vacuum or in a non-oxidizing

Application No.: 10/593,624 Amendment under 37 CFR §1.116

Art Unit: 1794 Attorney Docket No.: 062926

atmosphere to [[700°C]] 800°C to 1,200°C during physical alloy film formation or/and the following heat treatment, so as to grow crystal grains and form R-element-rich grain boundary phases.